



BJA
MAGNETICS

Bonded Alnico Grades

Grade	Remanence		Coercivity				Energy Density	
	Br		Hcb		Hcj		BHmax	
	mT	Gs	KA/m	Oe	KA/m	Oe	KJ/m ³	MGOe
Alnico 7/8	340	3400	72	900	84	1050	7.0	0.88
Alnico 8/10	350	3500	80	1000	96	1200	8.0	1.00