



**BJA**  
MAGNETICS

**Bonded Ceramic Grades**

Grade	Remanence		Coercivity				Energy Density		Max
	Br		Hcb		Hcj		BHmax		Op Temp
	mT	Gs	KA/m	Oe	KA/m	Oe	KJ/m3	MGOe	°C
FB1I	63	630	50	640	165	2100	1.0	0.13	120
FB3I	135	1350	85	1060	175	2200	3.2	0.40	120
FB1A	240	2400	175	2200	240	3000	11.0	1.38	120
FB2A	290	2900	190	2380	226	2840	16.0	2.01	120