



BJA
MAGNETICS

Injection Molded Ceramic Grades

Grade	Remanence		Coercivity				Energy Density		Max
	Br		Hcb		Hcj		BHmax		Op Temp
	mT	Gs	KA/m	Oe	KA/m	Oe	KJ/m ³	MGOe	°C
GSP-T04	110-130	1100-1300	70-85	880-1068	190-230	2388-2890	1.5-3.0	0.2-0.4	140
GSP-T07	130-180	1300-1800	85-125	1068-1571	190-230	2388-2890	3.0-6.0	0.4-0.8	140
GSP-1.2	210-240	2100-2400	120-170	1508-2136	160-230	2011-2890	7.0-12.0	0.9-1.5	140
GSP-1.5	250-260	2500-2600	165-195	2073-2450	210-320	2639-4021	11.0-13.0	1.4-1.6	140
GSP-1.8	270-280	2700-2800	170-200	2136-2513	210-320	2639-4021	14.3-15.1	1.8-1.9	140
GSP-2.0	280-290	2800-2900	180-190	2262-2388	210-320	2639-4021	15.9-16.5	2.0-2.1	140